

## SUPERCONDUCTIVITY IN THE Sn-Ba-Sr-Y-Cu-O SYSTEM

K.S.Aleksandrov, B.P.Khrustalev, S.N.Krivomazov,  
M.I.Petrov, A.D.Vasilyev, and S.A.Zwegintsev

Kirensky Institute of Physics, USSR Academy of Sciences,  
Siberian Branch, 660036 Krasnoyarsk, USSR

Since Bednorz and Müller /1/ discovered high- $T_c$  superconductivity in the La-Ba-Cu-O compound, several families of superconducting oxides have been synthesized /2/. In this paper we report the results of search for superconductivity in the compounds based on tin which has a lone electron pair like Bi, Tl, Pb.

The following compounds were synthesized:  $\text{Sn}_1\text{Ba}_1\text{Sr}_1\text{Cu}_3\text{O}_x$ ,  $\text{Sn}_1\text{Ba}_1\text{Ca}_1\text{Cu}_3\text{O}_x$ ,  $\text{Sn}_1\text{Ba}_1\text{Mg}_1\text{Cu}_3\text{O}_x$ ,  $\text{Sn}_1\text{Sr}_1\text{Ca}_1\text{Cu}_3\text{O}_x$ ,  $\text{Sn}_1\text{Sr}_1\text{Mg}_1\text{Cu}_3\text{O}_x$ ,  $\text{Sn}_1\text{Ca}_1\text{Mg}_1\text{Cu}_3\text{O}_x$ . The initial components were oxides and carbonates of the appropriate elements. Standard firing-grinding procedure was used. Final heating was carried out at  $960^\circ\text{C}$  during 12 hours. Then the samples were cooled inside the furnace. All the synthesis cycles were carried out in air atmosphere.

Among the synthesized compounds only  $\text{Sn}_1\text{Ba}_1\text{Sr}_1\text{Cu}_3\text{O}_x$  showed remarkable conductivity ( $\rho \sim 10 \text{ Ohm}\cdot\text{cm}$ ). Other compounds were practically dielectrics ( $\rho > 1000 \text{ Ohm}\cdot\text{cm}$ ). Presence of a possible superconductivity in  $\text{Sn}_1\text{Ba}_1\text{Sr}_1\text{Cu}_3\text{O}_x$  was defined by using the Meissner effect. At low temperature a deviation from paramagnetic behaviour is observed. The hysteresis loops obtained at lower temperatures undoubtedly testify to the presence of a superconductive phase in the sample. However, the part of the superconductive phase in the  $\text{Sn}_1\text{Ba}_1\text{Sr}_1\text{Cu}_3\text{O}_x$  ceramic turned out to be small, less than 2%, which agrees with the estimation from magnetic data. In order to increase the content of the superconductive phase two-valent cations Ba, Sr were partially substituted by univalent (K) and three-valent ones (Y). Two samples were obtained:  $\text{Sn}_1\text{Ba}_{0.7}\text{Sr}_{0.7}\text{K}_{0.7}\text{Cu}_3\text{O}_x$  and  $\text{Sn}_1\text{Ba}_{0.7}\text{Sr}_{0.7}\text{Y}_{0.7}\text{Cu}_3\text{O}_x$ . The former is a typical paramagnet without any anomaly down to 4.2K. The latter has shown the magnetic and electric properties undoubtedly indicating the presence of a superconductivity phase with the onset temperature  $T_c \approx 55\text{K}$ . The superconductive properties of the sample do not seem to be caused by the phase  $\text{YBaSrCu}_3\text{O}_7$  /3/. This conclusion follows from the study of the  $\text{Sn}_2\text{Sr}_2\text{Ba}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$  and  $\text{Sn}_2\text{Ba}_2\text{Sr}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$  samples that were synthesized by analogy with the recent communications on superconductivity in  $\text{Pb}_2\text{Sr}_2(\text{Y}, \text{Ca})_1\text{Cu}_3\text{O}_8$  /4,5/. One may expect equal probability of the  $\text{YBaSrCu}_3\text{O}_7$  content for both samples, however their electrical properties are quite different. The compound  $\text{Sn}_2\text{Sr}_2\text{Ba}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$  is a good dielectric while  $\text{Sn}_2\text{Ba}_2\text{Sr}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$  has clearly expressed superconductive properties /6/. The magnetic moment was measured in an external field  $H = 100 \text{ Oe}$ . At  $T < 86\text{K}$  the sample exhibits a clearly defined diamagnetic behaviour characteristic of superconductors. At these temperatures the hysteresis loop has the form typical of high- $T_c$  superconductors. The amount of the superconductive phase in this sample, as a magnetic estimation in powder, is  $\sim 15\%$  of the volume of the sample.

A comparative analysis of the X-ray powder diagrams leads us to believe that the main motive of the  $\text{Y}_1\text{Ba}_2\text{Cu}_3\text{O}_7$  structure is preserved in the structure of  $\text{Sn}_2\text{Ba}_2\text{Sr}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$ . The unit cell parameters are:  $a = 4.1 \text{ \AA}$ ,  $c = 12.4 \text{ \AA}$  (or multiple).

We have also used the same procedure for  $\text{Sn}_1\text{Ba}_2\text{Sr}_{0.5}\text{Y}_{0.5}\text{Cu}_3\text{O}_x$ . The sample is a typical paramagnet without any anomaly down to 4.2 K.

The presence of superconductivity in the system based on tin allows us to suggest that other cations, besides the well-known Bi, Tl, Pb, having the lone electron pair effect, should also form superconductive compounds. If we limit ourselves to consideration of copper-containing oxides, we may suppose that definite alkali-earth ions (or their combination) would suit for each of the ions: Hg, Sb, In, ... in order to form a superconductive phase.

#### References

1. J.C.Bednorz and K.A.Müller, Z.Phys.B 64 (1986) 189.
2. A.W.Sleight, Science 242 (1988) 1519.
3. Y.Takeda, R.Kanno, O.Yamamoto, M.Takano, Z.Hiroi, Y.Bando, M.Shimada, H.Akinaga, and K.Takita, Physica C 157 (1989) 358.
4. M.A.Subramanian, I.Gopalakrishnan, C.C.Torardi, P.L.Gai, E.D. Boyes, T.P.Askew, R.B.Flippen, W.E.Farneth, and A.W.Sleight, Physica C 157 (1989) 124.
5. R.I.Cava, M.Marezio, I.I.Krajewski, W.F.Peck Jr., A.Santoro, and F.Beech, Physica C 157 (1989) 272.
6. K.S.Aleksandrov, B.P.Khrustalev, S.N.Krivomazov, M.I.Petrov, A.D.Vasilyev, and S.A.Zwegintsev, Physica C, submitted.